

Woodtype **PEAR steamed**

Description 3 layers of the same hardwood. Due to the steaming with vitalized Grander water, the Pear with partial heartwood receives a warm, reddish brown colour. The sorting Design ist slightly to very knotty, with a medium structure.

Brinell hardness 4,5 kp
 Gross density 0,72 g | cm³

1-Strip Country House Flooring PEAR steamed Design Systemboard „Lissabon”



Fixlength 1100 mm

SURFACES

- Oil | wax oxidative dried
- Varnished 7-times
- Untreated sanded
- Bevel



Symbol picture - may vary in colour and structure

Sorting guidelines	
Healthy knots	allowed (partly filled)
Black knots	allowed (partly filled)
Healthy red heart	allowed
Healthy black heart	allowed
Cracks	allowed (partly filled)
Curlted Spots differences in structure	allowed
Natural colour differences	allowed
Natural fiber orientation	allowed
Wormholes and insect-ate-spots	not allowed
Sapwood	not allowed
Red or brown spots	allowed
Stains from storage and light blueness	allowed
Knocked spots	not allowed
Mirror	allowed

Technical data						
Thickness	15 mm	Useful layer approx. 5 mm				
Width	150 mm					
Length	Fixlength	8 layers 1100 mm				
	(8 layers pkg)					
Connection	Tongue and groove					
<table border="1" style="width: 100%;"> <tr> <td>m² pkg. 1,32</td> <td>m² pal. 64,68</td> </tr> <tr> <td>kg pkg. 12</td> <td>kg pal. 588</td> </tr> </table>			m² pkg. 1,32	m² pal. 64,68	kg pkg. 12	kg pal. 588
m² pkg. 1,32	m² pal. 64,68					
kg pkg. 12	kg pal. 588					
<input checked="" type="checkbox"/> Floating laying <input checked="" type="checkbox"/> Glued laying <input checked="" type="checkbox"/> Suitable for underfloor heating when gluing the entire area with solvent-free adhesives						



Symbol picture - may vary in colour and structure